

INSULROOF SP FIRE-RATED GLASS-FACED INSULATION

Description

InsulRoof SP (InsulFoam SP) is an engineered insulation consisting of a superior closed-cell, lightweight and resilient expanded polystyrene (EPS) with a durable and stable, factory-laminated coated glass facer. InsulRoof SP is available in a nominal density of 1lb/ft³ or 1.25lb/ft³, and meets or exceeds the requirements of ASTM C578, Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation. In addition, InsulRoof SP offers a long-term, stable R-value and has excellent dimensional stability, compressive strength and water resistance properties.

Uses

InsulRoof SP is specifically designed for low-sloped roof applications that employ mechanically fastened or ballasted TPO, PVC and EPDM, as well as low-sloped built-up, modified bitumen and fully adhered single-ply roofs that incorporate cover boards or slip sheets. InsulRoof is also designed for use in fully-adhered fleeceback systems with compatable adhesives. Please consult local building codes and membrane manufacturers for system requirements.

Advantages

- Labor Savings. With a factory-laminated facer, InsulRoof SP saves labor time and reduces overall project costs, when incorporated into a roofing system that would otherwise require a slip sheet.
- Code Approvals. Insulfoam insulations are recognized in the International Code Council Evaluation Service (ICC-ES), and have numerous Underwriters Laboratory and Factory Mutual Approvals. Please contact your local Insulfoam representative for details.
- Environmentally Friendly. It does not contain any ozonedepleting blowing agents, may contain recycled material, and is 100% recyclable if ever removed or replaced.
- Stable R-value. The product's thermal properties will remain stable over its entire service life. There is no thermal drift, so the product is eligible for an Insulfoam 20-year thermal performance warranty.
- Proven Performance. EPS has been manufactured using the same chemistry since the mid-1950s, providing proven performance.
- Water Resistance. InsulRoof SP does not readily absorb moisture from the environment.



Sizes

InsulRoof SP is available in several standard thicknesses. Non-standard sizes may also be ordered; InsulRoof SP can be made up to a thickness of 6" (R-26), with a minimum thickness of 2" for 1 lb/ft³ insulation and 1.5" for 1.25 lb/ft³ insulation.

Typical Physical Properties*

Typical Filyereal Filoportics			
Property	Test Method	Value	
Density (nom. pcf)	ASTM C303	1.00	1.25
R-Value (Resistance) - per inch (hr•ft²•°F)/BTU @ 25 °F @ 40 °F @ 75 °F	ASTM C518 or ASTM C177	4.35 4.17 3.85	4.55 4.25 3.92
C-Value (Conductance) - per inch BTU/(hr•ft²•°F) @ 25 °F @ 40 °F @ 75 °F	ASTM C518 or ASTM C177	0.230 0.240 0.260	0.220 0.235 0.255
Compressive Strength (psi, 10% deformation)	ASTM D1621	10-14	13-18
Flexural Strength (min. psi)	ASTM C203	25	30
Dimensional Stability (maximum %)	ASTM D2126	2.0	2.0
Water Vapor Permeance (max. perm., 1 inch)	ASTM E96	5.0	3.5
Water Absorption (max. % vol.)	ASTM C272	4.0	3.0

^{*}Properties are based on data provided by resin manufacturers, independent test agencies and Insulfoam.