



Standard Specification for Rigid Cellular Polystyrene Geof foam¹

This standard is issued under the fixed designation D6817/D6817M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the types, physical properties and dimensions of rigid cellular polystyrene intended for use as geof foam.

1.2 This specification does not cover the layout, placement and workmanship for proper installation and performance of rigid cellular polystyrene geof foam.

1.3 Rigid cellular polystyrene geof foam covered by this specification may need protection from certain chemicals, environmental exposure, and concentrated loads. Additional design considerations may include thermal conductivity and buoyancy. Guidelines regarding these end use considerations are included in [Appendix X1](#).

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[C165 Test Method for Measuring Compressive Properties of Thermal Insulations](#)

[C203 Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation](#)

[C303 Test Method for Dimensions and Density of Preformed Block and Board-Type Thermal Insulation](#)

¹ This specification is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.03 on Permeability and Filtration.

Current edition approved May 1, 2013. Published May 2013. Originally approved in 2002. Last previous edition approved in 2013 as D6817-13. DOI: 10.1520/D6817_D6817M-13A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[C390 Practice for Sampling and Acceptance of Thermal Insulation Lots](#)

[C578 Specification for Rigid, Cellular Polystyrene Thermal Insulation](#)

[D1621 Test Method for Compressive Properties of Rigid Cellular Plastics](#)

[D1622 Test Method for Apparent Density of Rigid Cellular Plastics](#)

[D2863 Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics \(Oxygen Index\)](#)

[D4439 Terminology for Geosynthetics](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

3. Terminology

3.1 Definitions:

3.1.1 Terms used in this specification are defined in Terminology [D4439](#).

3.1.2 *geof foam*—block or planar rigid cellular foam polymeric material used in geotechnical engineering applications.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *EPS, XX*—number designation for expanded polystyrene geof foam type(s) having a minimum density of XX kg/m³ [lb/ft³].

3.2.2 *XPS, XX*—number designation for extruded polystyrene geof foam type(s) having a minimum density of XX kg/m³ [lb/ft³].

3.2.3 *RCPS*—letter designation for EPS and XPS rigid cellular polystyrene geof foam covered by this specification.

4. Ordering Information

4.1 Acquisition documents shall specify the following:

4.1.1 Title, number and year of this specification.

4.1.2 Type, as per [Table 1](#), or minimum density required.

4.1.3 Total product volume required of each type, or minimum density.

5. Materials and Manufacture

5.1 RCPS geof foam shall be formed by the expansion of polystyrene resin beads or granules in a molding process (EPS)

TABLE 1 Physical Property Requirements of RCPS Geofoam⁴

Type	EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46	XPS20	XPS21	XPS26	XPS29	XPS36	XPS48
Density, min., kg/m ³ [lb/ft ³]	11.2 [0.70]	14.4 [0.90]	18.4 [1.15]	21.6 [1.35]	28.8 [1.80]	38.4 [2.40]	45.7 [2.85]	19.2 [1.20]	20.8 [1.30]	25.6 [1.60]	28.8 [1.80]	35.2 [2.20]	48.0 [3.00]
Compressive Resistance, min., kPa [psi] at 1 % strain	15 [2.2]	25 [3.6]	40 [5.8]	50 [7.3]	75 [10.9]	103 [15.0]	128 [18.6]	20 [2.9]	35 [5.1]	75 [10.9]	105 [15.2]	160 [23.2]	280 [40.6]
Flexural Strength, min., kPa [psi]	69 [10.0]	172 [25.0]	207 [30.0]	240 [35]	345 [50.0]	414 [60.0]	517 [75.0]	276 [40.0]	276 [40.0]	345 [50.0]	414 [60.0]	517 [75.0]	689 [100.0]
Oxygen index, min., volume %	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0	24.0

⁴ For products that have an external skin, testing shall be undertaken with skins intact.

or by the expansion of polystyrene base resin in an extrusion process (XPS). RCPS geofoam may be manufactured with reprocessed polystyrene foam (regrind).

5.2 RCPS geofoam shall be of uniform density and have essentially closed cells. RCPS geofoam is an organic material and is considered combustible. It should not be exposed to flames or other ignition sources.

6. Qualification Requirements

6.1 The physical properties listed in **Table 1** constitute the minimum product qualification requirements for commonly manufactured types of RCPS geofoam. The compressive resistance at 1 % strain is typically within the elastic limit of the geofoam product types in **Table 1** and is accepted as the compressive resistance to limit long-term deformation under structural load.

6.2 *RCPS Geofoam Types*—It is the users responsibility to specify the required type as in **Table 1** and to obtain supporting documentation regarding physical properties from the material supplier.

6.3 The compressive resistance properties in **Table 2** are provided for applications where compressive resistance requirements for intended end-use applications are beyond the elastic limit of geofoam.

NOTE 1—The application of sustained load to geofoam beyond the elastic limit will result in significant deflections beyond the values provided in **Table 2**.

6.4 *Combustibility Requirements*—All RCPS geofoam shall contain sufficient flame retardants to meet a minimum Oxygen Index as required in **Table 1**.

6.5 *Curing*—Unless otherwise specified in the contract, RCPS geofoam shall be cured for a minimum of 24 h before delivery and inspection.

7. Availability and Dimensional Tolerance

7.1 *Availability*—The RCPS geofoam materials covered by this specification are commonly available in the size range shown in **Table 3**. Specific RCPS geofoam block dimensions vary by manufacturer equipment characteristics.

7.2 *Dimensional Tolerance*—Unless otherwise specified, the acceptable length, width, thickness, flatness and squareness tolerance criteria on RCPS geofoam shall not exceed ± 0.5 %.

8. Damage and Degradation

8.1 *Damage*—RCPS geofoam as delivered to the project site shall have no defects that will adversely affect its service and workability qualities. Material units that manifest unacceptable surface or volumetric damage shall be replaced.

8.1.1 *Surface Damage*—Damage to load bearing RCPS geofoam surfaces shall be limited to less than 20 % of the equivalent load bearing area of the unit.

8.1.2 *Volume Damage*—Volumetric damage of RCPS geofoam shall be limited to less than 1 % of the volume of a single unit.

8.1.3 *UV (Ultra-Violet) Degradation*—Discoloration and dusting of RCPS geofoam caused by the extensive exposure to sunlight is a defect that will adversely affect its service and is grounds for rejection. Refer to **X1.6**.

9. Inspection

9.1 *Sampling*—Unless otherwise specified in the purchase order or contract, the material shall be sampled for inspection in accordance with Practice **C390**.

9.2 *Weight*—Determine the weight of selected full size units in accordance with Test Method **D1622**, or as specified.

9.3 *Dimensions*—Verify specified dimensions and tolerances, as prescribed in Test Method **D1622** and **7.2** of this specification.

9.4 *Density*—Compute the density of test samples in accordance with Test Method **D1622**.

10. Acceptance or Rejection

10.1 Material that fails to conform to this specification shall be rejected promptly in writing. The manufacturer or supplier shall have the right to re-inspect the rejected shipment and resubmit selected units for acceptance under tightened inspection.

TABLE 2 Additional Physical Property Requirements of RCPS Geofoam^{A,B}

Type	EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46	XPS20	XPS21	XPS26	XPS29	XPS36	XPS48
Density, min., kg/m ³ [lb/ft ³]	11.2 [0.70]	14.4 [0.90]	18.4 [1.15]	21.6 [1.35]	28.8 [1.80]	38.4 [2.40]	45.7 [2.85]	19.2 [1.20]	20.8 [1.30]	25.6 [1.60]	28.8 [1.80]	35.2 [2.20]	48.0 [3.00]
Compressive Resistance, min., kPa [psi] at 5 % strain	35 [5.1]	55 [8.0]	90 [13.1]	115 [16.7]	170 [24.7]	241 [35.0]	300 [43.5]	85 [12.3]	110 [16.0]	185 [26.8]	235 [34.1]	335 [46.6]	535 [77.6]
Compressive Resistance, min., kPa [psi] at 10 % strain ^A	40 [5.8]	70 [10.2]	110 [16.0]	135 [19.6]	200 [29.0]	276 [40.0]	345 [50]	104 [15.0]	104 [15.0]	173 [25.0]	276 [40.0]	414 [60.0]	690 [100.0]

^A If yield occurs prior to 10 % deformation, report compressive resistance and deformation at yield in addition to the compressive resistance at 1 %, 5 %, and 10 % deformation.

^B For products that have an external skin, testing shall be undertaken with skins intact.

TABLE 3 Common Manufactured Dimensions of RCPS Geofoam

Dimension, mm [in.]	All EPS Types	All XPS Types
Width	305 to 1219 [12 to 48]	406 to 1219 [16 to 48]
Length	1219 to 4877 [48 to 192]	1219 to 2743 [48 to 108]
Thickness	25 to 1219 [1 to 48]	25 to 102 [1 to 4]

11. Certification

11.1 Unless otherwise specified in the purchase order or contract, the manufacturer or supplier shall furnish third party certification that representative material has either been tested or inspected as directed in the specification and the requirements have been met. When specified in the purchase order or contract, a report of the test results shall be furnished.

12. Product Marking

12.1 The following shall be marked on each whole unit of product:

- 12.1.1 Manufacturers Identification,
- 12.1.2 Date of Manufacture,
- 12.1.3 Type, (See [Table 1](#)), and
- 12.1.4 Weight, or Density.

13. Test Methods

13.1 Conditioning:

13.1.1 Samples shall be conditioned at a standard laboratory temperature of 23 ± 2°C [73.4 ± 4°F] for a minimum of 24 h prior to the start of tests.

13.2 *Dimensions and Density*—Test in accordance with Test Method [C303](#) or Test Method [D1622](#).

13.3 *Compressive Resistance*—Test in accordance with Test Method [C165](#) or Test Method [D1621](#) using 50 mm [2 in.] cubes. The rate of cross-head movement shall be 5.0 ± 0.5 mm/min [0.2 ± 0.02 in./min] equivalent to 10 % strain per minute.

13.4 *Flexural Strength*—Test in accordance with Test Method [C203](#).

13.5 *Oxygen Index*—Test in accordance with Test Method [D2863](#).

14. Precision and Bias³

14.1 The precision of this test method is based on an interlaboratory study of [13.3](#) of Specification D6817, conducted in 2011. A total of seven laboratories participated in this study, testing three materials at 1 %, 5 %, and 10 % compressive resistance. Each “test result” reported represents an individual determination, and all participants were asked to report five test results for each area tested. Practice [E691](#) was followed for the design and analysis of the data; the details are given in ASTM Research Report No. RR: D35-1014.

14.1.1 *Repeatability limit (r)*—Two test results obtained within one laboratory shall be judged not equivalent if they differ by more than the “r” value for that material; “r” is the interval representing the critical difference between two test results for the same material, obtained by the same operator using the same equipment on the same day in the same laboratory.

14.1.1.1 Repeatability limits are listed in [Tables 4-6](#).

14.1.2 *Reproducibility limit (R)*—Two test results shall be judged not equivalent if they differ by more than the “R” value for that material; “R” is the interval representing the critical difference between two test results for the same material, obtained by different operators using different equipment in different laboratories.

14.1.2.1 Reproducibility limits are listed in [Tables 4-6](#).

14.1.3 The above terms (repeatability limit and reproducibility limit) are used as specified in Practice [E177](#).

14.1.4 Any judgment made in accordance with statements [14.1.1](#) and [14.1.2](#) would have an approximate 95 % probability of being correct.

14.2 *Bias*—As there were no available standard reference materials at the time of this study, bias cannot be determined.

14.3 The precision statement was determined through statistical examination of 315 test results, submitted by seven laboratories, recording compressive resistance measurements of three materials.

14.3.1 The three materials were all described as expanded polystyrene.

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D35-1014.

TABLE 4 1 % Compressive Resistance (units)

Material	Average ^A \bar{x}	Repeatability Standard Deviation S_r	Reproducibility Standard Deviation S_R	Repeatability Limit r	Reproducibility Limit R
A	4.564	0.333	0.647	0.933	1.812
B	9.855	0.381	1.144	1.068	3.203
C	21.591	0.850	2.310	2.379	6.467

^A The average of the laboratories' calculated averages.

TABLE 6 10 % Compressive Resistance (units)

Material	Average ^A \bar{x}	Repeatability Standard Deviation S_r	Reproducibility Standard Deviation S_R	Repeatability Limit r	Reproducibility Limit R
A	12.660	0.532	0.701	1.490	1.962
B	22.051	0.510	0.609	1.427	1.705
C	46.705	1.080	1.343	3.023	3.760

^A The average of the laboratories' calculated averages.

TABLE 5 5 % Compressive Resistance (units)

Material	Average ^A \bar{x}	Repeatability Standard Deviation S_r	Reproducibility Standard Deviation S_R	Repeatability Limit r	Reproducibility Limit R
A	11.021	0.480	0.631	1.344	1.767
B	19.956	0.454	0.527	1.270	1.474
C	42.664	0.932	1.152	2.610	3.226

^A The average of the laboratories' calculated averages.

14.4 To judge the equivalency of two test results, it is recommended to choose the material that is closest in characteristics to the test material.

15. Keywords

15.1 block; board; cellular polystyrene; EPS; expanded polystyrene; extruded polystyrene; foam plastic; geofoam; RCPS; reprocessed; rigid cellular polystyrene; XPS

APPENDIX

(Nonmandatory Information)

X1. END-USE CONSIDERATIONS

X1.1 Thermal Resistance

X1.1.1 RCPS geofoam also functions as a thermal insulation. The thermal insulation properties of RCPS geofoam are as specified in Specification C578, and may impact the end use design of applications subject to different exposure conditions. Consult the RCPS geofoam manufacturer for specific recommendations.

X1.2 Solvent Exposure

X1.2.1 RCPS geofoam must be protected from petroleum based solvents and their vapors. Examples of these solvents are: gasoline, diesel fuel, concrete curing compound, coal tar pitch, and asphaltic mastic compounds.

X1.3 Equipment Traffic

X1.3.1 Equipment traffic that can impose contact pressures in excess of the allowable design stress for RCPS geofoam should be restricted. Protective materials such as sheathing or planks may be placed on the material to allow light rubber-tired equipment use.

X1.4 Buoyancy

X1.4.1 RCPS geofoam becomes buoyant when submerged in water and adequate ballast must be provided to resist expected uplift forces.

X1.5 Design

X1.5.1 The design and installation of RCPS geofoam is the responsibility of the user.

X1.5.2 RCPS geofoam can be supplied precut to specified dimensions to fit specific project needs. Desired shapes and sizes can also be field cut with a hot wire, saw, or other cutting tool.

X1.6 Ultra-Violet Degradation

X1.6.1 Discoloration and dusting of load bearing surfaces of RCPS geofoam caused by extended exposure to sunlight shall be removed by pressure washing.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).